



## TEST REPORT

**Client** Booth Ventures Ltd

**Address** Harwood Quarry Landfill Site  
Brookfold Lane  
Harwood  
Bolton  
BL2 4LT

**Contract** Ravenhead

**Job Number** MRN 2576/9  
**Date of Issue** 04 October 2016  
**Page** 1 of 5

### Approved Signatories

S J Hutchings, A W Hutchings, A Richardson

### Notes

- 1 All remaining samples and remnants from this contract will be disposed 28 days from the date of this report unless you notify us to the contrary.
- 2 Result certificates, in this report, not bearing a UKAS mark, are not included in our UKAS accreditation schedule.
- 3 Opinions and interpretations expressed herein are outside the scope of our UKAS accreditation
- 4 Certified that the samples have been examined and tested in accordance with the terms of the contract/order and unless otherwise stated conform to the standards/specifications quoted. This does not, however, guarantee the balance of the materials from which the tested samples have been taken to be of equal quality.



**TEST CERTIFICATE**  
**PARTICLE SIZE DISTRIBUTION**  
 BS EN 933-1 : 1997 (Washing & Sieving Method)


Determination of water content in accordance with BS EN 1097-5:2008

CLIENT	Booth Ventures Ltd
SITE	Ravenhead
JOB NUMBER	MRN 2576/9

SAMPLE LABEL	10mm Pipe Bedding	DATE SAMPLED	26-Sep-16
LAB SAMPLE No	67973	DATE RECEIVED	27-Sep-16
DATE TESTED	28-Sep-16	SAMPLED BY	Client

MATERIAL	10mm Pipe Bedding
ADVISED SOURCE	Ravenhead Quarry

Sieve Size (mm)	% Passing (%)	Specification (%)	Sieve Size (mm)	% Passing (%)	Specification (%)
125	100		6.3	35	
90	100		5	18	
80	100		4	11	
75	100		2	7	
63	100		1.18	7	
50	100		1	7	
40	100		0.6	7	
31.5	100		0.5	7	
28	100		0.425	7	
20	100		0.3	7	
16	100		0.25	7	
14	100		0.15	6	
10	81		0.125	6	
8	56		0.063	4.0	



REMARKS

As received moisture content = 5.8%

SIGNED

NAME

S.J. Hutchings  
(Director)

DATE

04-Oct-16