



TEST CERTIFICATE
PARTICLE SIZE DISTRIBUTION

BS EN 933-1 : 1997 (Washing & Sieving Method)


Determination of water content in accordance with BS EN 1097-5:2008

CLIENT	Booth Ventures Ltd
SITE	Adswood
JOB NUMBER	MRN 2576/3

SAMPLE LABEL	6F5	DATE SAMPLED	Not advised
LAB SAMPLE No	66776	DATE RECEIVED	17-Jun-16
DATE TESTED	18-Jun-16	SAMPLED BY	Client

MATERIAL	6F5
ADVISED SOURCE	Adswood

Sieve Size (mm)	% Passing (%)	Specification (%)	Sieve Size (mm)	% Passing (%)	Specification (%)
125	100	100	6.3	22	
90	100		5	20	
80	99	75-99	4	19	
75	94		2	16	0-35
63	87		1.18	14	
50	65		1	14	
40	50	50-90	0.6	12	
31.5	43		0.5	12	
28	38		0.425	11	
20	30	30-75	0.3	9	
16	26		0.25	8	
14	25		0.15	6	
10	24	15-60	0.125	5	
8	23		0.063	4.1	0-12



REMARKS

Sample complies with the advised grading specification 6F5 (SHW 2016)

As received moisture content = 6.8%

SIGNED

NAME

A. Richardson
 (Laboratory Manager)

DATE

23-Jun-16